

Company Silverhook
Brand Silverhook Fuel Efficient
Product PCEO 0W-20
Status Compliant

Case No VLS010227

17/04/2025 This case was accepted by VLS

23/09/2025 The case concerned compliance with the following market standards.

1.SAE J300 specifies that the Low Temperature Pumping Viscosity for an SAE 0W-20 grade should be < 60 000 mPa.s at -40°C and that no Yield Stress should be observed. On the sample analysed a Low Temperature Pumping Viscosity of 68400 mPa.s at -40°C was recorded and a Yield Stress <105 g was observed, which does not meet the requirements of the SAE, ACEA, API and OEM specifications claimed for the product.

2.ACEA C5 & C6 mandates a phosphorus content of between 0.07 and 0.09%, a level of 0.06% was determined on the sample analysed.

VLS accepted the case and procured a sample of the product for testing. The test results showed that the sample was compliant for Phosphorous content at 789 mg/kg or 0.0789%, but was not compliant for Yield Stress at -40 degrees centigrade measured at <105g, or Apparent Viscosity at -40 degrees centigrade measured at 74,200 m.Pa.s.

In response Silverhook stated that they had amended the formulation prior to the VLS investigation which would bring the product back into compliance and these actions had been agreed with a third party. On the basis of assurances given by the third party that the case had been closed, VLS is content to close the investigation subject to a six month review in line with its stated process.